

Report

Product: Cystallit CL-8

Regarding: UNI EN 1186-5

Materials and articles in contact with foodstuffs - Plastics.
Based on UNI EN 1186-5 2003
Test methods for overall migration into aqueous food simulants by cell.

Result: Cystallit CL-8 is applied processed in accordance with the current valid technical data sheet. The following test results were determined:

Food simulant	Test conditions	Overall migration in mg/dm ²
Distilled water	2h at 40°C	<0,1
Acetic acid 3% (m/V)	2h at 40°C	0,6
Ethanol 10% (V/V)	2h at 40°C	<0,1
Isooctane	2h at 40°C	<0,1
Ethanol 95%	2h at 40°C	43,1

Accredited Institute: Catas test report 190846

Note: Coatings for Wood Coatings in accordance with the Standard UNI EN 1186-05; 2003 is not regulated, it is a voluntary, legally non-binding examination, which is based on the rules.

Hilden 08.03.2019



I. Münch

Wood Interior 2K solutions