

Report

Product: Cystallit CL-TM

Regarding: UNI EN 1186-5

Materials and articles in contact with foodstuffs - Plastics.
Based on UNI EN 1186-5 2003
Test methods for overall migration into aqueous food simulants by cell.

Result: Cystallit CL-TM is applied processed in accordance with the current valid technical data sheet. The following test results were determined:

| Food simulant | Test conditions | Overall migration in mg/dm ² |
|----------------------|-----------------|---|
| Distilled water | 2h at 40°C | <0,1 |
| Acetic acid 3% (m/V) | 2h at 40°C | 0,6 |
| Ethanol 10% (V/V) | 2h at 40°C | 0,1 |
| Isooctane | 2h at 40°C | 0,3 |
| Ethanol 95% | 2h at 40°C | 8,9 |

Accredited Institute: Catas test report 244194

Note: Coatings for Wood Coatings in accordance with the Standard UNI EN 1186-05; 2003 is not regulated, it is a voluntary, legally non-binding examination, which is based on the rules.

Hilden 08.03.2019



I. Münch
Wood Interior 2K solutions